

PORON® Urethane Foams

*Typical Product Properties*

**PORON® 92 Extra Soft – Slow Rebound**

PROPERTY	TEST METHOD	VALUE	
<b>PHYSICAL</b>			
Density, lb. / ft <sup>3</sup> (kg /m <sup>3</sup> )	ASTM D 3574-95, Test A	12 (192)	15 (240)
Tolerance, %		± 10	
Thickness, inches (mm)		0.155 - 0.425 (3.94 - 10.80)	0.125 - 0.500 (3.18 - 12.70)
Tolerance, %		± 10	
Standard Color (Code)		Black (04)	
Compression Force Deflection, psi (kPa)	0.2" / min. Strain Rate Force Measured @ 25% Deflection	0.25-2.5 (1.7 - 17)	0.3 - 3.5 (2 - 24)
Typical psi (kPa)		1.4 (10)	2 (14)
Hardness, Durometer, Shore "O",	ASTM D 2240-97	< 3	< 5
Compression Set, % max.	ASTM D 1667-90 Test D @ 73°F (23°C) ASTM D 3574-95 Test D @ 158°F (70°C) ASTM D 3574-95 Test J/Test D autoclaved 5 hrs @ 250°F (121°C)	2	10
Resilience by Vertical Rebound, %	ASTM D 2632-96	4	5
Dimensional Stability, % max. change	22 hrs @ 176°F (80°C) in a forced-air oven	± 3	± 5
Tensile Strength, Min. psi (kPa), Typical psi (kPa)	ASTM D 3574-75 Test E	12 (83) -	15 (103) 30 (207)
Tensile Elongation, % min., Typical	ASTM D 3574-75 Test E	150 -	120 206
Tear Strength, Min. pli (kN/m), Typical pli (kN/m)	ASTM D 264-91 Die C	2 (0.4) -	4 (0.7) 5 (0.9)
<b>ELECTRICAL AND THERMAL</b>			
Dielectric Constant, K' ("DK")	ASTM D 150 measurements at 72°F (22°C) relative humidity 50% for 24 hrs.	-	1.48
Dielectric Strength, volts/mil	ASTM D 149-97a	42	50
Dissipation Factor, tan D ("DF")	ASTM D 150-98	-	0.04
Volume Resistivity, ohm-cm	ASTM D 257-99	-	8 x 10 <sup>11</sup>
Surface Resistivity, ohm/sq.	ASTM D 257-99	-	10 x 10 <sup>11</sup>
Coefficient of Thermal Expansion		2.3 - 3.1 x 10 <sup>-4</sup> in./in./°C	

**PORON® 92 Extra Soft – Slow Rebound Continued**

PROPERTY	TEST METHOD	VALUE	
Density, lb. / ft <sup>3</sup> (kg /m <sup>3</sup> )	ASTM D 3574-95, Test A	12 (192)	15 (240)
<b>TEMPERATURE RESISTANCE</b>			
Recommended Constant Use, max.	SAE J-2236	194°F (90°C)	
Recommended Intermittent Use, max.		250°F (121°C)	
Embrittlement	ASTM D 746-98	-4°F (-20°C)	
<b>FLAMMABILITY AND OUTGASSING</b>			
Flammability	UL 94HBF (File E20305) (Pass ≥)	.155" (3.94mm)	.118" (3.0mm)
	MVSS 302 (Pass ≥)	.155" (3.94mm)	.118" (3.0mm)
	CSA Comp HBF (File 188149) (Pass ≥)	.155" (3.94mm)	.118" (3.0mm)
Fogging	SAE J-1756 3 hrs @ 212°F (100°C)	Pass	
Outgassing, Total Mass Loss (TML) %	ASTM E 595-93 24 hrs @ 257°F (125°C) @ <7x10 <sup>3</sup> Pa	0.76	1.73
Outgassing, Collected Volatile Condensable Materials (CVCM) %		0.04	0.14
Outgassing, Water Vapor Regain (WVR) %		0.60	0.71
<b>ENVIRONMENTAL</b>			
Gasketing and Sealing	UL JMST2 (Consisting of UL50 and UL508) CAN/CSA – C22.2 No. 94-M91	-	File MH15464
Water Absorption, High Humidity Exposure, % weight gain, typical	AMS 3568-95	2	
Water Absorption, Immersion Testing, % weight gain, typical	ASTM D 570-95	38	34
Mildew/Bacteria Resistance	ASTM G 21	Good	
Staining	ASTM D 925	No Stain	
Skin Contact Irritation	Primary Skin Irritation Test (FHSA)	Pass	

These materials are unsupported and should be processed with the knowledge that stretching of die cut parts can occur when material has not been relaxed.

Notes:

1. – represents testing not available at this time.
2. All metric conversions are approximate.
3. Additional technical information is available.
4. Typical values should not be used for specification limits.



1-800-773-0062  
www.marianinc.com

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foam Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foam Materials for each application. The Rogers logo, The world runs better with Rogers, and PORON are licensed trademarks of Rogers Corporation. © 2000-2003, 2006, 2008, 2009, 2012 Rogers Corporation, All rights reserved. Printed in U.S.A 0612-PDF, Publication # 17-038