8/14/2019 Datasheet





www.marianinc.com 1-800-773-0062

MELINEX® 339

Product Description

MELINEX® 339 is an opaque white polyester film with superb handling properties that is pre-treated on both surfaces to promote adhesion to most industrial coatings.

Typical Applications

MELINEX® 339 is used as a base for pressure sensitive labels, photographic printing paper, in security and access cards, in multiple use tickets and in general printing applications.

Approvals

UL recognized - Product has been registered with Underwriters Laboratories

Typical Properties

Typical Froperties											
Available Thickness [Gauge]											
200;	300;	380;	500;	700;	1000						

Property	Thickness	Value	Units	Test						
OPTICAL										
Gloss 45 Degrees	200-1000	40	%	ASTM D1003						
Gloss 60 Degrees	200-1000	45	%	ASTM D1003						
Total Light Transmission (TLT)	200	12	%	ASTM D1003						
Total Light Transmission (TLT)	300	9	%	ASTM D1003						
Total Light Transmission (TLT)	500	6	%	ASTM D1003						
Total Light Transmission (TLT)	1000	2	%	ASTM D1003						
Whiteness	200	100		ASTM E313-79						
Whiteness	300	100		ASTM E313-79						
PHYSICAL										
Elongation at Break MD	200-1000	115	%	ASTM D882A						
Elongation at Break TD	200-1000	90	%	ASTM D882A						
Tensile Strength MD (break)	200-1000	16,000	psi	ASTM D882A						
Tensile Strength MD 5%	200-1000	12,000	psi	ASTM D882A						
Tensile Strength TD (break)	200-1000	19,000	psi	ASTM D882A						
Yield Strength TD 5%	200-1000	12,000	psi	ASTM D882A						
THERMAL										
Shrinkage MD (190°C)	200	2.8	%	Unrestrained @ 190°C/5 min						
Shrinkage MD (190°C)	300-1000	1.5	%	Unrestrained @ 190°C/5 min						
Shrinkage TD (190°C)	200	1.0	%	Unrestrained @ 190°C/5 min						
Shrinkage TD (190°C)	300-1000	1.5	%	Unrestrained @ 190°C/5 min						

Contact Info

DuPont Teijin Films U.S. Limited Partnership 3600 Discovery Drive Chester, VA 23836 USA

Tel: (800) 635-4639 Fax: (804) 530-9867

Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as 8/14/2019 Datasheet

additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body (DuPont Teijin Films Medical Policy). For other medical applications, see the Medical Caution Statement. DuPont Teijin Films accepts no liability for use of it's products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® STTM are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Tetoron® are registered trademarks of Teijin Limited used under license by DuPont Teijin Films U.S. Limited Partnership. Teonex® is a registered trademark of Teijin DuPont Films Japan Limited and is used under license by DuPont Teijin Films U.S. Limited Partnership.