High Performance Foams Division



www.rogerscorp.com

BISCO® Silicones

Typic al Product Properties

BISCO® A2 Sound Barrier

BISC O® A2 Sound Barrier is a solid silic one rubber engineered to meet demanding requirements for flammability, smoke density and toxic ity. A2 is used to block the transmission of sound and demonstrates excellent performance in low frequency noise reduction. Innovative filler technology is used to create superior flame resistance meeting the radiant panel flammability test FAR25.856(a).

Applic a tions:

- Airc raft a c o ustic insulation
- No ise reduction liner for interior panels
- Airc raft flooring no ise barrier
- Rail interior no ise blocker

Availability (rolls)

- Are al Densities (Surface Weight) from 1.2
 kg/m² to 8.2 kg/m²
- Standard width 1000mm
- Standard roll length 5m
- Samples available upon request

Specific ations

Airbus ABS5708

| Pre lim inary Te c hnic a l Data | | |
|--|--|---|
| Properties . | Typic al Value s | Te st Me tho ds |
| Po lyme r Typ e | VMQ | ISO 1629 |
| Color | Light Gray | |
| De nsity | 1.64 g/c m ³ | ISO 2781 |
| Hard ne ss | 62 Shore A | ISO 868 |
| Tensile Strength | 2.8 MPa | ISO 37 Type 2 |
| Elongation at Break | 220 % | ISO 37 Type 2 |
| Te ar Strength | 10.2 N/mm | ISO 34 Me tho d C |
| Temperature Stability | -50° C to + 180° C | |
| Fire Resistance | | |
| Fla m m a b ility | Pass JAR/FAR, Part 25 25.853(a) Change 15/Amdt. 25-91 | JAR/ FAR, Part 25, App. F Part I, Para (a) (1) (ii) |
| Flame Propagation Resistance | Pass FAR, Part 25 25.856(a) | FAR, Part 25, App. F Part VI |
| Flame Penetration Resistance in Bonded Condition | Pass JAR/FAR, Part 25 Change 15/Amdt. 25-60, 25.855(c) and App. FPart III | JAR/ FAR, Part 25, Change 15/ Amdt. 25- 60, App. F Part III |
| Smoke Gas Components | Pass | AIIM 3.0005. |
| Smoke Density | Pass | JAR/ FAR 25, App. F, Part V & AIIM 2.0007 |

Product Matrix

- Standard Width 1000mm
- Standard Roll Length 5m (other roll size s available on request)
- Minimum Order Quantity 5m
- Surface Weight (Are a Density) Availability
 1.2 kg/m² (0.25 lb s/ft²)
 to 8.2 kg/m² (1.68 lb s/ft²)
- Specifications
 Airbus ABS 5708

| Standard Surface Weight (Area Density) | | |
|--|---------|--|
| kg/m^2 | Lbs/ft² | |
| 1.2 | 0.25 | |
| 1.5 | 0.31 | |
| 2.3 | 0.47 | |
| 3.0 | 0.61 | |
| 3.5 | 0.72 | |
| 4.7 | 0.96 | |
| 5.9 | 1.21 | |
| 7.0 | 1.43 | |
| 8.2 | 1.68 | |
| Other surface weights available on request | | |

The information contained in this Data Sheet is intended to assist you in designing with Rogers' High Performance Foams. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' High Performance Foams for each application. The Rogers logo, The world runs better with Rogers, and BISCO are licensed trade marks of Rogers Corporation. © 2009, 2011 Rogers Corporation, All rights reserved. Printed in U.S.A., 0411-PDF, Publication #180-251