

FyreWrap® LiB Films

Introduction

FyreWrap® LiB (Lithium-ion Battery) Film from Unifrax is a high-temperature, lightweight flame barrier and electrically insulating material designed to increase safety in lithium-ion battery packs. Based on proprietary fire blocking technology, the film was developed as a flame barrier for applications demanding extremely lightweight materials.

FyreWrap LiB Film Features

- Fire resistant, flame barrier
- Electrically insulating
- Suitable for temperatures in excess of 1100°C
- Uniform lightweight flexible sheets
- Easy to wrap, shape or cut
- Fully heat-sealable with ultrasonic or thermal sealing equipment
- Designed for minimum moisture absorption and reduced installed weight

Film Capabilities

- Aid in thermal runaway propagation prevention
- Short circuit prevention and electrical protection
- Cascading fire prevention
- Thermal isolation and containment

Applications

- Battery Enclosures / Lids
 - Aluminum, Steel, Copper, and other metals
 - Composites
- Bus bars, current collectors
- Battery sub-components where high voltage electrical and fire protection are needed
- Packaging



Material Properties

- Resistant to temperatures in excess of 1100°C
- Thickness: 0.2 mm
- Basis Weight: 100-200 g/m²
- Burst Strength: > 340 kPa
- Puncture Resistance (10 mm probe): > 50 N
- Permeance: < 0.2 perms
- UL94 V-0
- ASTM E1461 Flash Method Thermal Conductivity: 0.202 (W/m-K)
- Dielectric Strength ASTM D149-09 (2013): 700-800 (volts/mil) / 20 (kV/mm)
- 60 Hz Dielectric Constant ASTM D150-11: 1.97 DC 0.0087 (DF)
- 10 kHz Dielectric Constant ASTM D150-11: 2.08 DC 0.0071 (DF)
- Arc Resistance ASTM D495-14: 14.0
- Volume and Surface Resistivity ASTM D257-14:
 - Volume Resistivity: 5.36e+14 (ohm-cm)
 - Surface Resistivity: 1.07e+11 (ohms/square cm)

Please contact Unifrax for more information on FyreWrap LiB films and coatings along with any specific design requirements.

The following is a registered trademark of Unifrax: FyreWrap.

The test data shown are average results of tests conducted under standard procedures and are subject to variation. Results should not be used for specification purposes. Product Information Sheets are periodically updated by Unifrax. Before relying on any data or other information in this Product Information Sheet, you should confirm that it is still current and has not been superseded. A Product Information Sheet that has been superseded may contain incorrect, obsolete and/or irrelevant data and other information.