

Technical Data Sheet

P-THERM®

PS-1513

Product Description:

P-THERM® PS-1513 is a hyper-soft silicone based thermally conductive gap filler with an embedded fiberglass support and 125 micron removable polyester carrier.

Construction / Properties:

	Property	V alue			Test Method	
General	Color	Green			Visual	
	Thickness Range	0.5 mm - 5.0 mm			ASTM D374	
	Reinforcement Carrier Type	Fiberglass				
	Density (g/cc)	2.51			ASTM D792	
	Heat Capacity (J/g K) @ 50 C	0.84			ASTM E1269	
	Hardness (Shore 00)	14			ASTM D2240	
	Total Mass Loss (@ 125 C/24 hrs)	0.06%			ASTM E595**	
	Flammability Rating	V-0			UL 94	
	Continuous Use Conditions	-60 - 200 C			QSP-754	
		Value				
cal	Property	Value			Test Method	
ctrical	Property Dielectric Breakdown Strength (kV/mm)	Value 9.88			Test Method ASTM D149	
Electrical		_				
	Dielectric Breakdown Strength (kV/mm)	9.88			ASTM D149	
	Dielectric Breakdown Strength (kV/mm) Volume Resistivity (ohm-cm)	9.88 1.0E+18			ASTM D149 ASTM D257	
ermal	Dielectric Breakdown Strength (kV/mm) Volume Resistivity (ohm-cm) Property	9.88 1.0E+18 Value 3 W/m K	rformance vs.	Strain	ASTM D149 ASTM D257 Test Method	
	Dielectric Breakdown Strength (kV/mm) Volume Resistivity (ohm-cm) Property	9.88 1.0E+18 Value 3 W/m K	rformance vs. 20	Strain 30	ASTM D149 ASTM D257 Test Method	


Thermal conductivity tested at 20% strain.

Thermal Impedance (K cm²/W) @ Imm

3.81

3.23

4.42



^{**} Tested at atmospheric pressure

^{**} Values tested include interfacial thermal resistance: Application performance is directly related to surface roughness, flatness and pressure applied.

Features:


- Good Thermal Conductivity
- Excellent Compression Characteristics
- Excellent Wet-Out
- Superb Flexibility
- Excellent Converting Properties
- RoHS and HF Compliant





Applications:


- LED Lighting
- Battery Components
- Infotainment Modules
- Smartphones
- Tablets
- Computers
- Digital Personal Assistants
- Automotive Lighting

















Specific tests should be performed by the end user to determine the product stability for the particular application.

For Additional Information:

E-mail: sales@polymerscience.com
Toll Free: +1 888.533.7004
Web: www.polymerscience.com
Revision: 040621



