

Technical Data Sheet

P-THERM®

PS-2641

Product Description:


P-THERM® PS-2641 is a silicone based thermally conductive gap filler with an embedded fiberglass support and 125 micron removable polyester carrier.

Construction / Properties:

	Property	Value			Test Method	
General	Color	Gray			Visual	
	Thickness Range	0.5 mm - 5.0 mm			ASTM D374	
	Reinforcement Carrier Type	Fiberglass				
	Density (g/cc)	1.82			ASTM D792	
	Heat Capacity (J/g K) @ 50 C	0.97			ASTM E1269	
	Hardness (Shore 00)	22			ASTM D2240	
	Total Mass Loss (@ 125 C/24 hrs)	0.15%			ASTM E595**	
	Flammability Rating	V-0			UL 94	
	Continuous Use Conditions	-60 - 200 C			QSP-754	
Electrical	Property	Value			Test Method	
	Dielectric Breakdown Strength (kV/mm)	12.00			ASTM D149	
	Volume Resistivity (ohm-cm)	1.0E+09			ASTM D257	
	Property	Value			Test Method	
Thermal	Thermal Conductivity	I W/m K			ASTM D5470*	
	Thermal Performance vs. Strain					
	Deflection (% Strain)	10	20	30	ASTM D5470***	
	Thermal Impedance (K cm²/W) @ Imm	10.99	9.94	9.08		

^{*} Thermal conductivity tested at 20% strain.


^{***} Values tested include interfacial thermal resistance: Application performance is directly related to surface roughness, flatness and pressure applied.



^{**} Tested at atmospheric pressure


Features:


- Good Thermal Conductivity
- Excellent Compression Characteristics
- Excellent Wet-Out
- Superb Flexibility
- Excellent Converting Properties
- RoHS and HF Compliant





Applications:


- LED Lighting
- Battery Components
- Infotainment Modules
- Smartphones
- Tablets
- Computers
- Digital Personal Assistants
- Automotive Lighting














Specific tests should be performed by the end user to determine the product stability for the particular application.

For Additional Information:

040621

Revision:

E-mail: sales@polymerscience.com
Toll Free: +1 888.533.7004
Web: www.polymerscience.com



P) LYMER
SCIENCE, INC.

www.marianinc.com